

Protective Coating



OTHER *M-LINE* COATINGS COMPATIBLE WITH GAGEKOTE #1:

- Gagekote #5
- Epoxylite #813

DESCRIPTION

Solvent-thinned (toluene) synthetic resin. Often used as a precoat for Gagekote #5, and Epoxylite #813. Resistant to

moisture and offers a wide operating temperature range. Provides limited mechanical protection. Convenient to use.

CHARACTERISTICS

Operating Temperature Range:
–320° to +850°F [–195° to +455°C].

Shelf Life:
2 years at +75°F [+24°C].

Cure Requirements:
Single coat air dry for 15 minutes at +75°F [+24°C]. Prior to encapsulation by other coatings, air dry 4 hours at +75°F [+24°C] or 30 minutes at +150°F [+65°C] to prevent solvent entrapment.

PACKAGING OPTIONS

Kits:
1 brush-cap bottle [1 oz/30 ml]
12 brush-cap bottles [1 oz/30 ml each]
1 bottle [8 oz/240 ml each]