

Protective Coating



OTHER M-LINE COATINGS COMPATIBLE WITH GAGEKOTE #5:

- M-Coat W-1 Wax
- M-Coat B

DESCRIPTION

Two-part 100%-solids modified polysulfide epoxy. Good for general laboratory and field use. Prime leadwire insulation with M-Coat B. Excellent mechanical protection. Resistant to

salt water, gasoline, hydrocarbon oils, most acids, alkalines, and solvents.

CHARACTERISTICS

Operating Temperature Range:

–90° to +250°F [–68° to +120°C].

Shelf Life:

1 year at +75°F [+24°C].

Cure Requirements:

Air dry 6 hours at +75°F [+24°C] or 1 hour at +150°F [+66°C].

PACKAGING OPTIONS

Kits:

4 jars Part A [1.5 oz/45 gm]

4 jars Part B [0.5 oz/15 gm]

1 jar Part A [11 oz/340 gm]

1 jar Part B [3.5 oz/114 gm]