

Protective Coating



OTHER *M-LINE* COATINGS COMPATIBLE WITH GAGEKOTE #8:

- Gagekote #5
- Gagekote #7

DESCRIPTION

Single component transparent acrylic coating. Recommended as an under or over coating for Gagekote #5, and Gagekote #7. Good for anchoring intra-bridge wiring in high

performance transducers. Extremely flexible and resistant to direct water immersion, mild solvents and chemicals. Film thickness of 0.005 - 0.01 in. [0.1 - 0.25mm] per coat.

CHARACTERISTICS

Operating Temperature Range:

–100° to +270°F [–75° to +130°C].

Shelf Life:

1 year at +75°F [+24°C].

Cure Requirements:

Single coat air dry for 10 minutes at +75°F [+24°C]. Prior to encapsulation by other coatings, air dry 4 hours at +75°F [+24°C] or 30 minutes at +150°F [+65°C] to prevent solvent entrapment.

PACKAGING OPTIONS

Kits:

- 1 brush-cap bottle [1 oz/30 ml]
- 12 brush-cap bottles [1 oz/30 ml each]
- 1 bottle [8 oz/240 ml]
- 1 bottle [32 oz/960 ml]