

Protective Coating



FEATURES

- Excellent protection from moisture
- Low reinforcement
- Easy to apply

DESCRIPTION

Solvent-thinned butyl rubber designed to provide excellent moisture protection with low reinforcement effects. Principally used in transducers. Exhibits a paste-like consistency

and is normally applied with a spatula. Thickness over 0.1 in [2.5 mm] not recommended.

CHARACTERISTICS

Cure Requirements:

Air dry 8 hours, followed by an elevated temperature cure of +150° to +175°F [+65° to +80°C] for 4 to 6 hours.

Operating Temperature Range:

0° to +175°F [-20° to +80°C].

Shelf Life:

12 months at +75°F [+24°C].

PACKAGING OPTIONS

Kit:

75 g collapsible tubes, 4 each

Bulk:

Quart container